PLAINTIFF'S EXHIBIT UC-801

UV-001 #14

BUSINESS CONFIDENTIAL

INTERIM REPORT

SIZING ASBESTOS: SCREENING DISPERSED SUSPENSIONS

Author: S. Chwastiak

Date: June 29, 1967

Notebook No.: 1730, pp. 19-29

SUMMARY

Dispersed suspensions of asbestos can be sized by using screens whose nominal sizes range from 200 mesh to 10 microns.

The results of fine screening reflect the degree of liberation more accurately than the present technique of screening flocculated suspensions on a 65-mesh sieve.

Preliminary data show a correlation between screening results and viscosity measurements.

INTRODUCTION

It has become apparent during the attempts to make silica-treated asbestos that the degree of liberation of the feed is one of the most critical factors in the process. The program to study the method of evaluation of liberation was begun in September, 1966, and it was learned that screening could be carried out with very fine screens provided that the asbestos was dispersed with an excess of anionic surfactant. It has been proposed subsequently that a feed containing less than 4% of particulate matter which is large enough to be retained on a 10-micron screen is suitable for making silica-treated asbestos.

During a recent visit by the author to the King City mill, this problem was discussed with the staff there. It was decided that fine screening of dispersed asbestos suspensions should be evaluated to see if this technique could be substituted for the present method of screening of flocculated suspension on a 65-mesh screen. Using the latter procedure, it is difficult for different people to obtain the same results on the same sample. The retention on the screen is due both to the presence of large particles and also to the degree of coherence of flocs. Some of the flocs, however, are susceptible to breakdown by rather weak mechanical forces, so small variations in screening technique cause significant differences in results. Screening of dispersed suspensions should eliminate the errors normally caused by the presence of flocculated material.

Research and Development Department
Chemicals & Plastics
Operations Division
Union Carbide Corporation
Niagara Falls, New York

RECEIVED
JUL. 14 1967
J. W. BIDDLE

Published by AsbestosClaims.Law
asbestosclaims.law/library/16024/1

It has been predicted that if the size distribution of opened asbestos had a slope of 1 on a Schuhmann plot, and the top size of the asbestos was 65 mesh, as little as 1% of the fibers may be liberated, and 99% of the weight of the asbestos would occur as bundles of fibers.(1) Accordingly, the characteristics of the size distribution of asbestos slurries opened in the Waring Blendor for various times would also be useful to check this theory.

A rapid method of estimating the degree of asbestos liberation would be highly desirable for plant control, so the viscosities of asbestos suspensions opened for different times were measured with the Fann Viscometer.

Mr. E. J. Markiewicz carried out the 65-mesh screening, and Dr. K. Park conducted the viscosity measurements.

DISCUSSION

Repulping High Purity Pellets

Four aliquots of 2% slurry of High Purity Asbestos were opened in the Tappi Standard Disintegrator, made by the Herman Manufacturing Company, for 1, 2, 4, and 8 minutes. Each slurry was checked for plus 65 mesh by the standard way, and then dispersed samples of the slurries were screened on 200-mesh, 325-mesh, 25-micron, and 10-micron sieves. The results are shown in Table I.

It is obvious that any of the fine screens can be used, but the 25-micron or 10-micron screen would be preferred since the results are more accurate if significant proportions of the samples are retained on the screens.

Opening Asbestos in a Waring Blendor

Standard-grade pellets were used in these tests since they contain much asbestos which has never been opened. The pellets were broken down by mixing a 2% slurry for 8 minutes in the Herman opener.

Three hundred milliliter portions of the slurry were opened for 0, 1, 2, and 3 minutes at natural pH in the small Waring Blendor. Another portion was opened for 3 minutes after acidifying with acetic acid to pH 4. The opened slurries were sized on a series of fine screens, and the data are also presented in Table I.

It is apparent that the data from 65-mesh screens do not reflect adequately the improvements in liberation with increasing opening time in the Waring Blendor. However, the data obtained by screening dispersed asbestos suspensions on a 10-micron sieve do show progressive differences.

It is interesting to note that there is a great improvement in the effectiveness of liberation when a Waring Blendor is used as the opening device with a dispersed suspension, compared to the use of a Waring Blendor with a flocculated suspension.

The unique characteristic of the size distribution data is that there is a surprisingly small difference between the amount of the same sample retained on screens ranging from 200 mesh to 10 microns. A Schuhmann plot of these data would have a very small slope. Similar sizing data for a brittle solid would likely have a slope of one on a Schuhmann plot.

Union Carbide trial exhibit UC-801: S. Chwastiak, Interim Report on Sizing Asbestos by Screening Dispersed Suspe... Published by AsbestosClaims.Law
ACL Doc 16024 · Page 2 of 20 asbestosclaims.law/library/16024/2

The viscosities of the opened, flocculated suspension were measured under a large number of conditions. The best data were obtained with bob-rotor R1-B1 at a shear rate of 170 $sec.^{-1}$ Higher shear rates were not as good for differentiating between the viscosities of the various suspensions. The viscosity data are shown in Figure 1a. A definite correlation has been found with the amount of +10 micron material in the suspension and the viscosity of the suspension. This is shown in Figure 1b. More studies of the reproducibility of such data will have to be made before the value of the viscosity can be classed as a reliable and useful measure of liberation.

S. Chwastiak

S. Chwastiak

SC:dag

REFERENCE

(1) Progress Report, Mining and Metals Division, Niagara Falls, New York, September 15, 1966, by S. Chwastiak


Union Carbide trial exhibit UC-801: S. Chwastiak, Interim Report on Sizing Asbestos by Screening Dispersed Suspe... Published by AsbestosClaims.Law
ACL Doc 16024 · Page 3 of 20 asbestosclaims.law/library/16024/3

TABLE I

Results of Screening Asbestos Suspensions

Material	Opening Time, minutes		Retention on Screen, %						
			65 mesh 208μ		200 mesh 74μ	325 mesh 44μ		25μ	10μ
	Herman	Waring Blendor	flocc'd.	disp'd.					
	1	0	41	0.1	34	47	49	52	58
HPP	2	0	15	0.3	12	27	30	30	45
2% susp.	4	0	3	0.5	3	22	20	16	25
	8	0	1.5	0.3	3	15	6	10	13
	8	0	8.3	-	25	33		32	35
SG P	8	1	0.5	-	6.3	13		13	16
2% susp.	8	2	0.1	-	4.0	7.8		8.3	12
	8	3	0.01	-	1.5	5.5		5.8	9.3
SG P	8	3 at	-	-	-	2.0		2.6	4.6
2% susp.		pH 4.0							

(a)



(b)




FIGURE 1 - Correlation Between Viscosity and:

(a) Opening in Waring Blendor

(b) Fraction Retained on 10-Micron Sieve

Suspension - 2% SGP pretreated 8 min. in Herman

DISTRIBUTION

BOUND BROOK

I. Allen
W. T. Higgins
W. Miller
P. E. Pratt
R. W. Quarles
P. A. Thomas
N. L. Zutty

NEW YORK

F. D. Dexter
L. P. Jehle
A. E. Pufahl
N. J. Setter
L. Shechter
J. Sidlovsky
J. F. Voit
J. R. Wilkinson

SOUTH CHARLESTON

J. W. Biddle
F. B. Brown
N. R. Eldred
R. I. Hoaglin
F. Johnson
C. S. Maxwell
C. W. McGary
J. J. Smith
F. J. Welch

TARRYTOWN

T. H. Welch

NIAGARA FALLS

R. E. Byrne
W. H. Blackwell
G. L. Dickson
R. A. Hard
B. L. Ingalls
M. S. Kisiel
E. J. Markiewicz
K. Park
J. E. Skvarla
F. H. Thompson
R. G. Woolery

TONAWANDA

S. Sterman

KING CITY

J. A. Riddle+
J. L. Myers

UV-0011 #10

INTERIM REPORT

G

MODIFIED HIGH PURITY ASBESTOS:

THE EVALUATION OF SILICA-TREATED ASBESTOS AND ALUMINA-SILICA-TREATED ASBESTOS AS PAPERMAKING ADDITIVES

Author: G. L. Dickson

Date March 21, 1967

Study No. 61

Notebook No. 1691

SUMMARY

Previous work has shown that laboratory prepared silica-treated asbestos and alumina-silica-treated asbestos are suitable as papermaking additives, and that for this purpose they possess properties which make them superior to unmodified High Purity Asbestos. The present work was intended to evaluate pilot plant samples of similar materials by incorporating them in laboratory handsheets. The results again indicate that these materials can be adopted for use as papermaking fillers, and that their optical properties approach those of our present Asbestos "T" product. The favorable results obtained from this work suggest that a more complete program for evaluating these materials and their method of preparation should be initiated as soon as possible.

INTRODUCTION

1. Pilot Plant Production

The pilot plant production of four samples of alumina silicate-treated asbestos was carried out under the supervision of Dr. S. Chwastiak. For convenience, his Progress Report of December 1966, covering the method of preparation, is attached. Basically, it consisted of treating 13 pounds of High Purity Asbestos with sodium silicate, followed by four levels of addition of aluminum acetate. Also included in his report are the results of the zeta potential measurements made on the various samples.

2. Samples Identification

The five samples were received by the Paper Laboratory in opened form, i.e., the dried filter cakes had been opened dry in a Mikro-pulverizer. The samples were identified as follows:

Research and Development Department
Chemicals & Plastics
Operations Division
Union Carbide Corporation
Niagara Falls, New York

RECEIVED
APR. 1 J 1967
J. W. BIDDLE

T-168

Published by AsbestosClaims.Law
asbestosclaims.law/library/16024/7

(1) 1684-25-1 Sodium silicate treated (0.38% Al_2O_3)
(2) 1684-25-2 Aluminum acetate treated (1.30% Al_2O_3)
(3) 1684-25-3 " " " (2.72% Al_2O_3)
(4) 1684-25-4 " " " (5.25% Al_2O_3)
(5) 1684-25-5 " " " (7.35% Al_2O_3)

(Numbers in parenthesis denote Al_2O_3 content as established by chemical analyses)

3. Evaluation of Samples

A. Brightness

Compressed pellets were formed from the five samples and the brightness (reflectance) determined using the Photovolt brightness meter. The following results were obtained:

Sample	Brightness
25-1	82.0
25-2	82.5
25-3	82.5
25-4	83.0
25-5	82.5

These values appear quite favorable in contrast to that of 74-76 usually obtained on our High Purity Product. Brightness measurements were also made on similar pellets which had been heat treated at two temperatures. As can be seen from the following, there is considerable color degradation in all cases.

Sample	Untreated	2 hr. at 500°C.	2 hr. at 700°C.
25-1	82.0	73.0	66.5
25-2	82.5	73.5	65.5
25-3	82.5	74.5	67.5
25-4	83.0	73.5	68.5
25-5	82.5	74.5	68.0

B. Thixotropy

Viscosity measurements were obtained on styrene-paraplex systems containing modified asbestos, which is the present method for determining the acceptability of RG-244. These results indicate that the sodium silicate-treated sample (1685-25-1) was of marginal quality, since a viscosity of 20,000 cps at 25°C. is usually considered as being minimal. For academic reasons, the aluminum acetate-treated samples were also included and, as was expected, produced poor results.

Union Carbide trial exhibit UC-801: S. Chwastiak, Interim Report on Sizing Asbestos by Screening Dispersed Suspe... Published by AsbestosClaims.Law
ACL Doc 16024 · Page 8 of 20 asbestosclaims.law/library/16024/8

	Viscosity Results (cps)	
Sample	45°C.	25°C.
25-1	12,500	17,000
25-2	500	3,000
25-3	300	1,500
25-4	300	900
25-5	300	1,100

C. Laboratory Handsheets

The compatibility of the various samples in a papermaking system was determined by incorporating them at 3 addition levels in laboratory handsheets. The Noble and Wood equipment (8" x 8" sheet mold) was used, utilizing a 100% bleached sulfite pulp beaten to 200 CSf. For comparative purposes, High Purity Asbestos, Asbestos "T", and titanium dioxide (King City Japanese) were also included in this program. All fillers were added dry in the open form to the pulp furnish in a Hermann Standard Disintegrator. Sufficient alum was also added at this point to obtain a pH of about 4.8-5.0 in the sheet mold. The handsheets were conditioned and tested according to standard methods. These results, plus the analytical data, are presented in Tables I and II.

From this cursory examination, it would appear that all samples are suitable as additives for paper. The only exception might be Sample 1684-25-5, which produced specks in the finished handsheets. As this could be a determining factor governing the use of these materials in paper, their pulpability characteristics were determined according to our standard method.

1. Pulpability

	+65 Fraction (%)			
Disintegrating time (min.)	2	4	6	8
25-1	*	*	*	*
25-2	0.026	0.004	*	*
25-3	0.058	0.032	0.074	0.032
25-4	0.756	0.456	0.128	*
25-5	9.294	7.012	5.458	4.625
High Purity	0.936	0.430	0.344	0.374

*Too low to measure

These results show that only Sample 25-5 is more difficult to repulp than our High Purity material. Based on this, it can be assumed that the other samples are acceptable in this respect.

Union Carbide trial exhibit UC-801: S. Chwastiak, Interim Report on Sizing Asbestos by Screening Dispersed Suspe... Published by AsbestosClaims.Law
ACL Doc 16024 · Page 9 of 20 asbestosclaims.law/library/16024/9

2. Filler retention

No attempt was made at this time to evaluate the self-retention properties of the various samples. However, based on the amount of filler retained in the handsheets, the indications are that the modified asbestos products are comparable to High Purity and Asbestos "T".

3. Bulk - Porosity - Smoothness

Basis weight and caliper determinations tend to indicate that an increase in bulk is obtained at the higher addition levels. Sheffield porosity was lower in most cases where the handsheets contained the modified products, while Sheffield smoothness results showed the wire side of the sheet to be generally smoother. In no instance is there enough data available to make generalizations regarding these properties.

4. Optical Characteristics

The brightness and opacity characteristics of sheets containing the modified asbestos products are quite good and approximate those of sheets containing Asbestos "T". The calculated light scattering coefficients (s_p), as presented in Table III, show that surface treatment improves the optical characteristics considerably. It should be noted, however, that again there is not enough data available to predict the exact value for each material, and that the reported figures are only approximations. This is quite evident from the extremely low results obtained on Sample 1684-25-5, which are probably due to the poor filler distribution experienced with this sample. The values obtained for High Purity Asbestos, Asbestos "T", and titanium dioxide are in line with those obtained by other investigators.

CONCLUSIONS

The results obtained from this study are encouraging enough to prompt further work with these materials. The next program will duplicate in some respects the present work in order to ascertain whether or not these results are reproducible. Also to be included are several production variables such as the influence of slurry pH on filtration rates, and the effects of filtering variables on end product characteristics. The latter is believed to be important as there is some evidence available which indicates that these are important variables in the production of RG-244. Also to be considered are the self-retention characteristics of silicate and alumina silicate-treated asbestos and their effect on the retention of other paperloading materials.

Gordon L. Dickson

Gordon L. Dickson

GLD/bsn
Attachments

Union Carbide trial exhibit UC-801: S. Chwastiak, Interim Report on Sizing Asbestos by Screening Dispersed Susp... Published by AsbestosClaims.Law
ACL Doc 16024 · Page 10 of 20 asbestosclaims.law/library/16024/10

Union Carbide trial exhibit UC-801: S. Chwastiak, Interim Report on Sizing Asbestos by Screening Dispersed Susp...
ACL Doc 16024 · Page 11 of 20

TABLE I

Handsheet Preparation Data and Analytical Results

Set Number	% Filler Added	pH (Sheet Mold)	% Ash	% TiO_2	% Mg	% Filler
1	Control	4.8	0.22	-	0.01	-
2	5% High Purity Asbestos	4.9	2.70	-	0.76	3.04
3	10% " " "	4.8	5.07	-	1.36	5.44
4	15% " " "	4.8	7.39	-	1.91	7.64
5	5% Titanium Dioxide	4.8	1.17	1.18	-	1.18
6	10% " "	4.8	2.06	2.11	-	2.11
7	15% " "	4.8	2.67	2.70	-	2.70
8	5% Asbestos "T"	4.8	2.60	0.78	0.49	2.74
9	10% " "	4.9	5.65	2.05	1.07	6.33
10	15% " "	4.8	8.26	2.48	1.50	8.48
11	5% 1684-25-1	4.9	2.51	-	0.63	2.80
12	10% "	4.9	5.59	-	1.37	6.09
13	15% "	4.8	7.02	-	1.74	7.74
14	5% 1684-25-2	4.8	2.60	-	0.63	2.86
15	10% "	4.8	4.70	-	1.13	5.12
16	15% "	4.8	7.22	-	1.81	8.21
17	5% 1684-25-3	4.8	2.22	-	0.55	2.59
18	10% "	4.9	4.81	-	1.18	5.55
19	15% "	4.8	6.91	-	1.62	7.62
20	5% 1684-25-4	4.8	2.11	-	0.47	2.29
21	10% "	5.0	5.13	-	1.21	5.89
22	15% "	5.0	7.29	-	1.68	8.18
23	5% 1684-25-5	4.9	1.91	-	0.47	2.36
24	10% "	5.0	4.52	-	1.07	5.37
25	15% "	4.9	7.37	-	1.72	8.63
26	Control	4.8	0.09	-	0.01	-

Published by AsbestosClaims.Law
asbestosclaims.law/library/16024/11

Union Carbide trial exhibit UC-801: S. Chwastiak, Interim Report on Sizing Asbestos by Screening Dispersed Susp...
ACL Doc 16024 · Page 12 of 20

TABLE II

Handsheet Physical Test Data

Set Number	Basis Weight	Bulk	Porosity	Smoothness (Felt/Wire)	Brightness	Opacity	R_o	R_w
1	58.87	2.14	166	400/350	75.3	71.5	60.2	84.7
2	60.10	2.09	136	400/350	74.3	72.6	61.0	84.3
3	60.28	2.08	130	400/340	73.5	74.5	62.1	83.8
4	59.01	2.07	129	400/320	73.2	74.9	62.1	83.6
5	57.91	2.12	148	400/340	80.0	75.3	65.0	86.1
6	58.73	2.15	180	400/340	81.0	78.5	67.5	86.4
7	57.68	2.16	169	400/340	82.0	79.3	68.4	86.9
8	58.96	2.13	149	400/320	77.6	76.8	65.2	85.4
9	60.19	2.11	145	400/320	78.5	83.4	70.8	85.4
10	60.10	2.12	138	390/310	79.2	86.7	74.2	85.6
11	60.19	2.13	119	400/340	77.2	76.7	65.0	85.1
12	58.73	2.23	113	400/330	77.6	82.2	69.5	84.8
13	59.50	2.21	109	390/320	78.4	84.0	71.1	85.0
14	59.37	2.20	131	400/330	77.5	76.1	64.8	85.2
15	59.60	2.21	116	400/320	78.9	81.2	69.1	85.3
16	59.50	2.24	118	400/290	79.6	84.4	72.0	85.3
17	58.60	2.21	140	410/320	78.5	75.6	64.7	85.5
18	58.91	2.23	125	410/310	79.6	81.6	69.5	85.6
19	59.46	2.24	122	390/300	80.4	84.5	72.1	85.5
20	59.60	2.14	126	400/350	78.7	74.9	64.6	85.5
21	58.37	2.25	116	400/340	78.5	80.1	68.2	85.4
22	58.82	2.25	112	400/330	79.4	83.9	71.2	85.2
23	57.82	2.24	155	410/350	78.4	72.0	60.9	85.6
24	57.00	2.26	150	400/340	79.0	77.4	65.5	85.5
25	58.00	2.29	131	400/340	79.6	82.2	69.9	85.4
26	58.00	2.15	171	400/360	78.1	68.1	58.5	85.6

Published by AsbestosClaims.Law
asbestosclaims.law/library/16024/12

Union Carbide trial exhibit UC-801: S. Chwastiak, Interim Report on Sizing Asbestos by Screening Dispersed Susp...
ACL Doc 16024 · Page 13 of 20
Published by AsbestosClaims.Law
asbestosclaims.law/library/16024/13

TABLE III

Calculation of Optical Properties

Set Number	$C_{0.89}$	R_∞	s_W	s	k/s	k	k_p	s_p
1	71.1	0.80	1.65	280	0.02500	7.00	-	-
2	72.4	0.76	1.71	285	0.03789	2.57	84.2	395
3	74.1	0.79	1.83	304	0.02791	8.48	34.2	717
4	74.3	0.79	1.85	314	0.02791	8.76	30.1	720
5	75.5	0.83	2.01	347	0.01741	6.03	74.5	5932
6	78.1	0.85	2.22	378	0.01324	4.99	88.3	4929
7	78,7	0.85	2.35	407	0.01324	5.37	53.3	5000
8	76.3	0.81	2.06	349	0.02228	7.78	35.6	2810
9	82.9	0.83	2.72	452	0.01741	7.87	20.7	3002
10	86.7	0.84	3.13	521	0.01524	7.92	17.8	3125
11	76.4	0.80	2.07	344	0.02500	8.60	64.1	2571
12	82.0	0.82	2.57	438	0.01976	8.67	34.5	2874
13	83.6	0.83	2.82	474	0.01741	8.25	23.1	2791
14	76.1	0.81	2.00	337	0.02228	7.52	25.0	2273
15	81.0	0.83	2.52	423	0.01741	7.36	14.0	3066
16	84.4	0.83	2.95	496	0.01741	8.63	26.9	2911
17	75.7	0.82	1.99	340	0.01976	6.73	33.5	2587
18	81.2	0.83	2.56	434	0.01741	7.55	16.9	3063
19	84.3	0.83	2.95	496	0.01741	8.63	28.4	3110
20	75.6	0.82	1.98	332	0.01976	6.57	11.6	2533
21	79.9	0.82	2.38	408	0.01976	8.08	25.3	2445
22	83.6	0.83	2.83	481	0.01741	8.37	23.7	2738
23	71.1	0.81	1.66	287	0.02228	6.45	16.5	593
24	76.6	0.84	2.10	368	0.01524	5.59	19.2	1918
25	81.9	0.83	2.60	448	0.01741	7.80	16.2	2225
26	68.3	0.78	1.53	264	0.03103	8.18	-	-

PROGRESS REPORT

SUBJECT: PROPERTIES OF ASBESTOS Job No. 845-70301

WORK BY: S. Chwastiak, A. M. Gonas, W. A. Beccue

PERIOD ENDING: December 31, 1966

DATA FILED IN: NB 1685, p. 67; NB 1684, pp. 25, 26

SUMMARY

Alumina-silica-asbestos was prepared in the pilot plant. About 13 pounds of asbestos were treated with sodium silicate first, at a treatment level of 12.5 parts SiO_2 per 100 parts of asbestos. Aluminum acetate solution was added in stages, and large samples were taken after each addition. The final sample contained 7.35% Al_2O_3. Essentially, all of the aluminum added was recovered on the asbestos.

The silicate-treated asbestos surface was negatively charged above pH 3.5. A small addition of aluminum acetate made the surface even more negative in character, but further additions of aluminum acetate solutions resulted in products which had increasingly positively charged surfaces.

The various samples are being tested as paper additives by G. L. Dickson.

DISCUSSION

It was reported in the Progress Report dated July 15, 1966 that when silica-asbestos is treated with aluminum acetate, alumina is deposited on the surface. Electron microscope photographs were taken of the material from this test (1644-39). The silicate-treated asbestos is shown before treatment in Figure 1, and Figure 2 is a picture of the solid after the aluminum acetate treatment. The assay of this final product was 4.22% aluminum.

A large batch of aluminum acetate-treated material was made in the pilot plant. Twenty-five pounds of HPO asbestos in 200 gallons of water were opened further and then sized in a 30-mm. cyclone. The overflow was acidified with acetic acid and then further sized in a 10-mm. cyclone. Approximately 13 pounds of colloidal asbestos were obtained in 150 gallons of slurry. This suspension was treated with sodium silicate at a rate of 12.5 lb. of SiO_2 per 100 lb. of asbestos. Aluminum acetate was added in stages, and samples of suspension were taken after each addition. The samples were adjusted to pH 9 with sodium hydroxide before filtering in a small (1 ft. x 1 ft.) plate and frame filter press containing three plates, under approximately 40 psi. The remaining slurry at the end of the test was filtered in a large press under approximately 50 psi.

Both the dried filter cake and the filtrate from each sample were chemically analyzed. Rough mass balances were made from these data and the results are shown in Table I. It is seen that nearly all of the silica and all of the alumina were present in the filter cake. There is some error in the analyses or in the assumptions on which the calculations were based, since more alumina was found by assay of the solid than by calculation. However, the trend is clear; just about all of the aluminum acetate put into the suspension was abstracted by the silica-asbestos.

AUTHOR	DATE	WITNESSED BY	DATE
Kisoon Park/S. Chwastiak	1/6/67	J. E. Stewart	1/6/67

The various samples were opened dry in the Mikro-Pulverizer, and submitted to G. L. Dickson for testing as a paper additive. He will report on their effectiveness in paper later.

Portions of these samples were reslurried in water, and their surface properties were investigated by micro-electrophoresis. The data are shown in Figure 3. The silica-asbestos clearly is negatively charged above pH 3.5. For some unknown reason, adding a small amount of aluminum acetate causes the asbestos to become more negative. Further additions, however, cause the solid to become progressively more positively charged in nature. The electrophoretic data for asbestos and for the batch of treated asbestos prepared in the laboratory are shown for comparison.

AUTHOR	DATE	WITNESSED BY	DATE
Kicoon Park/S. Chwastiak	1/6/67	J. C. Edwards	1/6/67

Published by AsbestosClaims.Law

asbestosclaims.law/library/16024/15

Union Carbide trial exhibit UC-801: S. Chwastiak, Interim Report on Sizing Asbestos by Screening Dispersed Susp...
ACL Doc 16024 · Page 16 of 20

TABLE I

Aluminum Acetate Treatment of Silica-Asbestos in Pilot Plant, Run #25

No.	Operation	Wt. Asbestos Lb.		Vol. Susp. Gal.		pH	Sod. Silicate as SiO_2, lb.		Al Acetate as Al_2O_3, lb.		Chemical Analysis: Solution, g./l.			Chemical Analysis: Filter Cake, %			Cal. Amount on Asb., Parts per 100 Parts Asb.	
		Add	Cum.	Add	Cum.		Add	Cum.	Add	Cum.	Al_2O_3	MgO	SiO_2	Al_2O_3	MgO	SiO_2	Al_2O_3	SiO_2
1	Start, 10 mm. cyclone overflow		12.9		150	4.8												
2	Add 5.5 lb. sodium silicate solution (29.1% SiO_2)		12.9		150	9.1	1.60	1.60	none	none								
3	Take Sample 1684-25-1	-0.86	12.0	-10	140	9.1	-0.11	1.49	none	none	0.005	0.05	0.11	0.38	37.0	46.5	0	12.4
4	Add 8 l. Al acetate solution(1)		12.0	+ 2	142	7.1		1.49	+0.079	0.079								
5	Take Sample 1684-25-2	-0.68	11.3	- 8	136	7.1	-0.08	1.41	-0.004	0.075	0.005	0.02	0.11	1.30	36.3	45.4	0.665	12.5
6	Add 16 l. Al acetate		11.3	+ 4	140	6.2		1.41	+0.148	0.223								
7	Take Sample 1684-25-3	-0.81	10.5	-10	130	6.2	-0.10	1.31	-0.016	0.207	0.003	0.07	0.11	2.72	35.0	45.1	1.97	12.5
8	Add 24 l. Al acetate		10.5	+ 6	136	5.9		1.31	+0.238	0.445								
9	Take Sample 1684-25-4	-0.77	9.7	-10	126	5.9	-0.10	1.21	-0.033	0.412	0.007	0.05	0.09	5.25	33.8	43.4	4.25	12.5
10	Add 24 l. Al acetate		9.7	+ 6	132	5.7		1.21	+0.238	0.640								
11	Take Sample 1684-25-5	-0.73	9.0	-10	122	5.7	-0.09	1.12	-0.048	0.592	0.003	0.05	0.11	7.35	32.8	42.0	6.58	12.4
12	Add 2.6 l. of NaOH solution (4 M), then filter		9.0		122	9.6		1.12		0.592								

(1) Aluminum acetate solution contains 3 lb. salt in 20 gal. water


K. Park/S. Chwastiak 1/6/67

J. E. Skwarek 1/6/67

Published by AsbestosClaims.Law
asbestosclaims.law/library/16024/16

Union Carbide trial exhibit UC-801: S. Chwastiak, Interim Report on Sizing Asbestos by Screening Dispersed Susp...
ACL Doc 16024 · Page 17 of 20

Fig 3. Surface Properties of Silica-Asbestos Treated with Aluminium Acetate



Numbers on graph are Al assay of product

K Park/S. Chwastiak 1/6/67

J. P. Stranford 1/6/67

Page 6 of 6

Published by AsbestosClaims.Law
asbestosclaims.law/library/16024/17




FIGURE 1 - Silicate-Treated Asbestos

Test No. 1644-71-1 - Photo No. 4605 - Magnification 125,000X




FIGURE 2 - Aluminum Acetate-Treated Silica-Asbestos
Test No. 1644-39-1 - Photo No. 4501 - Magnification 150,000X

Published by AsbestosClaims.Law
asbestosclaims.law/library/16024/19

DISTRIBUTION

BOUND BROOK

I. Allen
W. T. Higgins
W. Miller
P. E. Pratt
R. W. Quarles
N. L. Zutty

NEW YORK

F. D. Dexter
L. P. Jehle
A. E. Pufahl
N. J. Setter
L. Shecter
J. Sidlovsky
J. F. Voit
J. R. Wilkinson

SOUTH CHARLESTON

J. W. Biddle ✓
F. B. Brown
N. R. Eldred
R. I. Hoaglin
F. Johnson
C. S. Maxwell
C. W. McGary
J. J. Smith
F. J. Welch

TARRYTOWN

T. H. Welch

GENEVA, SWITZERLAND

T. J. Hall

KING CITY

J. A. Riddle/
J. L. Myers

TONAWANDA

S. Sterman

NIAGARA FALLS

R. E. Byrne
W. H. Blackwell
S. Chwastiak
G. L. Dickson
R. A. Hard
B. L. Ingalls
M. S. Kisiel
E. J. Markiewicz
K. Park
J. E. Skvarla
F. H. Thompson
R. G. Woolery