UCC Paint Formulations - C. N. Carolina

~~Stanish~~ Dr. Miller & Sandell

PLAINTIFF'S EXHIBIT
UC-1015

A23145

UNION CARBIDE COATINGS MATERIALS

FORMULATION SUGGESTION E-1314A

EXTERIOR-INTERIOR PATCHING COMPOUND
"UCAR" LATEX 1234

APPLICATION INFORMATION

Ingredient	Pounds	Gallons
CHARGE INTO MIXER UNDER AGITATION:		
UCAR Latex 1234	825.0	92.6
TRITON	3.0	0.3
PMA-30	4.5	0.4
Vermiculite or Verxite #5(1)	50.0	2.2
TI-PURE R-901	30.0	0.9
Whiting #1	50.0	2.2
Asbestos Shorts(2)	50.0	2.3
	1012.5	100.9

PAINT PROPERTIES

PVC ---------- 15.0%
Solids ---------- 59.7%
Wt. per Gallon ---------- 10.0 Lbs.
Viscosity ---------- Trowel Consistency
Texture ---------- Coarse

(1) Zonolite Division, W. R. Grace Co.

(2) Asbestos 1422 - Whittaker, Clark and Daniels
Asbestos 7TF-1 - Johns-Manville

Caution: Contains asbestos fiber. Avoid creating dust. Breathing of asbestos dust may cause serious bodily harm.

A23140

This information is not to be taken as a warranty or representation for which we assume legal responsibility nor as permission or recommendation to practice any patented invention without a license. It is offered solely for your consideration, investigation and verification.

Union Carbide trial exhibit UC-1015: Union Carbide Coatings Materials Formulation Suggestions for Asbestos-Cont... Published by AsbestosClaims.Law
ACL Doc 16209 · Page 2 of 4 asbestosclaims.law/library/16209/2

UNION CARBIDE COATINGS MATERIALS

FORMULATION SUGGESTION I-1315A

SMOOTH MASONRY PATCHING COMPOUND
"UCAR" LATEX 1234

APPLICATION INFORMATION

Ingredients	Pounds	Gallons
CHARGE INTO MIXER UNDER AGITATION:		
UCAR Latex 1234	690.0	77.5
TRITON X 305	3.0	0.3
PMA 30	4.5	0.4
TI-PURE R-901	25.0	0.7
Whiting #1	350.0	15.5
Asbestos Shorts(1)	150.0	7.0
	1225.5	101.4

PAINT PROPERTIES

PVC ---------- 39.4%
Solids ---------- 72%
Wt. per Gallon ---------- 12.0 Lbs.
Viscosity ---------- Trowel Consistency
Color ---------- Greyish

(1) Asbestos 1422 - Whittaker, Clark and Danieds
Asbestos 7TF-1 - Johns-Manville

Caution: Contains asbestos fiber. Avoid creating dust. Breathing of asbestos dust may cause serious bodily harm.

A23147

This information is not to be taken as a warranty or representation for which we assume legal responsibility nor as permission or recommendation to practice any patented invention without a license. It is offered solely for your consideration, investigation and verification.

Union Carbide trial exhibit UC-1015: Union Carbide Coatings Materials Formulation Suggestions for Asbestos-Cont... Published by AsbestosClaims.Law
ACL Doc 16209 · Page 3 of 4 asbestosclaims.law/library/16209/3

FORMULATION SUGGESTION E-1329

EXTERIOR TEXTURED WALL COATING
UCAR® LATEXES 1234 AND 2345

	Pounds
UCAR Latex 1234	500.0
Water	45.0
"Nopcosant" K	2.0
PMA-30	3.0
Ethylene Glycol	10.0
"Dee-Fo" 97-2	3.0
"Ti-Pure" R-901	35.0
"Perlite" 8	100.0
UCAR Latex 2345	240.0
Asbestos Shorts 7TF-1[1]	65.0
Mineral Spirits	5.0
Sodium Bisulfite	3.0
Total	1011.0

CAUTION: Contains asbestos fiber. Avoid creating dust.
Breathing of asbestos dust may cause serious bodily harm.

[1] Asbestos 1422 — Whittaker, Clark & Daniels
Asbestos 7TF-1 — Johns-Manville

PAINT PROPERTIES

PVC	19.5%
Solids	58.0%
Weight per Gallon	10.0 lb.
Viscosity	90 to 100 K.U.

A23148

6/73-300 UCAR and UNION CARBIDE are registered trade marks of Union Carbide Corporation, U.S.A.

This information is not to be taken as a warranty or representation for which we assume legal responsibility nor as permission or recommendation to practice any patented invention without a license. It is offered solely for your consideration, investigation, and verification.

Union Carbide trial exhibit UC-1015: Union Carbide Coatings Materials Formulation Suggestions for Asbestos-Cont... Published by AsbestosClaims.Law
ACL Doc 16209 · Page 4 of 4 asbestosclaims.law/library/16209/4