CHEMTEX 1747 7th Avenue, Port Arthur, Texas 77642, (409) 983-4575

PLAINTIFF'S EXHIBIT

UC-1919

Project: Brownsville Tech Park, Union Carbide Batch Still Area, Browsville, Texas.

ASBESTOS BULK ANALYSIS AND IDENTIFICATION BY POLARIZED LIGHT MICROSCOPY

RESULTS OF ANALYSIS

CHEMTEX Number	Sample I.D.	Asbestos Present or Absent	Type of Asbestos	Other Fibrous Material Present	Non-Fibrous Material Present	Friable/ Non-Friable
9021797	1	Absent	None 0%	Fiber Glass 5%	Carbonaceous Material 95%	Friable
9021798	2	Absent	None 0%	Cellulose 3% Fiber Glass 5%	Carbonaceous Material 92%	Friable
9021799	3	Absent	None 0%	Cellulose 30%	Carbonaceous Material 70%	Friable
9021800	4	Absent	None 0%	Cellulose 15% Fiber Glass 1%	Carbonaceous Material 84%	Friable
9021801	5	Absent	None 0%	Cellulose 20%	Carbonaceous Material 80%	Friable
9021802	6	Absent	None 0%	Cellulose 30%	Carbonaceous Material 70%	Friable
9021803	7	Absent	None 0%	Cellulose 20% Fiber Glass 2%	Carbonaceous Material 78%	Friable

CNReddy

Dr. C. N. Reddy, Ph.D
Laboratory Director

CHEMTEX #: 9021797

BRD 1279

Published by AsbestosClaims.Law
asbestosclaims.law/library/16978/1

CHEMTEX 1747 7th Avenue, Port Arthur, Texas 77642, (409) 983-4575

Project: Brownsville Tech Park, Union Carbide Batch Still Area, Browsville, Texas.

ASBESTOS BULK ANALYSIS AND IDENTIFICATION BY POLARIZED LIGHT MICROSCOPY

RESULTS OF ANALYSIS

CHEMTEX Number	Sample I.D.	Asbestos Present or Absent	Type of Asbestos	Other Fibrous Material Present	Non-Fibrous Material Present	Friable/ Non-Friable
9021804	8	Absent	None 0%	Cellulose 10% Fiber Glass 2%	Carbonaceous Material 88%	Friable
9021805	9	Absent	None 0%	Cellulose 10% Fiber Glass 2%	Carbonaceous Material 88%	Friable
9021806	10	Absent	None 0%	Fiber Glass 3%	Carbonaceous Material 97%	Friable
9021807	11	Absent	None 0%	Cellulose 15% Fiber Glass 3%	Carbonaceous Material 82%	Friable
9021808	12	Absent	None 0%	Cellulose 20% Fiber Glass 5%	Carbonaceous Material 75%	Friable
9021809	13	Absent	None 0%	Cellulose 20% Fiber Glass 5%	Carbonaceous Material 75%	Friable

CNReddy

Dr. C. N. Reddy, Ph.D
Laboratory Director

CHEMTEX #: 9021797

BRD 1280

CHEMTEX 1747 7th Avenue, Port Arthur, Texas 77642, (409) 983-4575

Project: Brownsville Tech Park, Union Carbide
Batch Still Area, Browsville, Texas.

ASBESTOS BULK ANALYSIS AND IDENTIFICATION BY
POLARIZED LIGHT MICROSCOPY

RESULTS OF ANALYSIS

CHEMTEX Number	Sample I.D.	Asbestos Present or Absent	Type of Asbestos	Other Fibrous Material Present	Non-Fibrous Material Present	Friable/ Non-Friable
9021810	14	Absent	None 0%	Cellulose 3% Fiber Glass 5%	Carbonaceous Material 92%	Friable
9021811	15	Absent	None 0%	Cellulose 30% Fiber Glass 2%	Carbonaceous Material 68%	Friable
9021812	16	Absent	None 0%	Fiber Glass 10% Cellulose 30%	Carbonaceous Material 60%	Friable
9021813	17	Absent	None 0%	Cellulose 5% Fiber Glass 2%	Carbonaceous Material 93%	Friable

C N Reddy

Dr. C. N. Reddy, Ph.D
Laboratory Director

CHEMTEX #: 9021797

BRD 1281