PLAINTIFF'S EXHIBIT

UC-1922

UNION CARBIDE CORPORATION
INDUSTRIAL HYGIENE DEPARTMENT
P.O. BOX 186 PORT LAVACA
TEXAS 77979

FACSIMILE TRANSMITTAL COVER LETTER

PLEASE DELIVER THE FOLLOWING PAGES TO:

NAME: Ms. Belia Cortez
FIRM: Union Carbide Corp
CITY: Brownsville, TX
PHONE: (512) 831-4501
FAX: (512) 831-5278

TRANSMITTED FROM:

NAME: Alyce Hambleton (Jack [illegible])
FIRM: UNION CARBIDE CORPORATION, SEADRIFT PLANT
CITY: PORT LAVACA
PHONE: (512) 553-2091
UNICOM: 8-553-2091
FACSIMILE NUMBER (512) 553-2727

Rec'd 11:20 A.M. 5-15-90

DATE SENT: 5-15-90 TIME SENT: 11:15 AM

TOTAL NUMBER PAGES SENT 10 EXCLUDING COVER PAGE.

IF ALL THE PAGES ARE NOT TRANSMITTED, PLEASE CALL IMMEDIATELY.

OPERATOR'S NAME: ALYCE HAMBLETON PHONE: (512) 553-2091

SPECIAL INSTRUCTIONS:

BRD 1294

Kevco
LABORATORY & CONSULTING SERVICES

BULK ASBESTOS SAMPLE ANALYSIS REPORT

REPORT DATE: 5/14/90

TEST METHOD: 40 CFR CH. I (1-1-87 EDITION) PT 763, SUBPT. F APP. A. PAGES 293-299.

REPORT TO: UNION CARBIDE
P.O: BOX 186
PORT LAVACA Tx 77979
ATTENTION: CAL JONES

ANALYST SIGNATURE: Gary Landini
GARY LANDINI

KEVCO JOB NUMBER: DATE RECEIVED: DATE ANALYZED:	10402 5/14/90 5/14/90	10402 5/14/90 5/14/90	10402 5/14/90 5/14/90
CLIENT SAMPLE ID: PROJECT ID:	01	02	03
SAMPLE LOCATION:	#6 BOILER(VALVE) ASB. IN MATRIX ONLY	GAS TURBINE	GAS TURBINE (TRANSITION PIECE)
IS THE SAMPLE HOMOGENEOUS?	NO	NO	YES
DOES IT CONTAIN LAYERS?	YES	NO	NO
IS THE SAMPLE FIBROUS?	NO	YES	NO
SAMPLE COLOR:	WHITE/GRAY	TAN	WHITE
SAMPLE CONTAIN ASBESTOS FIBERS?	YES	NO	NO
ASBESTOS TYPE AND PERCENT:	CHRYSOTILE 01 - 02		
TOTAL PERCENT ASBESTOS:	TOTAL: 1 - 2	0 PERCENT	0 PERCENT
FIBROUS MATERIALS AND PERCENT:	FIBROUS GLASS 03 - 10 CELLULOSE 20 - 30	FIBROUS GLASS 50 - 60 CELLULOSE 01 - 05	FIBROUS GLASS 01 - 05 CELLULOSE 01 - 05
NONFIBROUS CONSTITUENTS:	BINDER, MATRIX	BINDER, GLASS BEADS	BINDER
DEVIATION FROM TEST METHOD:	*3		

- THIS TEST REPORT RELATES ONLY TO THE ITEMS TESTED AND MUST NOT BE REPRODUCED EXCEPT WITH THE APPROVAL OF THE LABORATORY.
- ALL SAMPLES WILL BE DISPOSED OF 90 DAYS FOLLOWING SAMPLE RECEIPT UNLESS OTHERWISE INSTRUCTED BY THE CLIENT.
- UNDER CURRENT EPA REGULATIONS, AN "ASBESTOS CONTAINING MATERIAL" CONTAINS MORE THAN ONE PERCENT ASBESTOS.

*3 SAMPLE RECEIVED WET, DRIED, MATRIX DISSOLVED IN TETRAHYDROFURAN, HEATED, EVAPORATED, THEN ANALYSIS CONTINUES ACCORDING TO TEST METHOD.

Kevco
LABORATORY & CONSULTING SERVICES

BULK ASBESTOS SAMPLE ANALYSIS REPORT

REPORT DATE: 5/14/90

TEST METHOD: 40 CFR CH. I (1-1-87 EDITION) PT 763, SUBPT. F APP. A. PAGES 293-299.

REPORT TO: UNION CARBIDE
P.O. BOX 124
PORT LAVACA TX 77979
ATTENTION: CAL JONES

ANALYST SIGNATURE: Gary Landin
GARY LANDIN

KEVCO JOB NUMBER: DATE RECEIVED: DATE ANALYZED:	10402 5/14/90 5/14/90	10402 5/14/90 5/14/90	10402 5/14/90 5/14/90
CLIENT SAMPLE ID: PROJECT ID:	04	05	06
SAMPLE LOCATION:	STEAM HEADER(NEXT TO CONTROL ROOM) ASB. IN MATRIX ONLY	FUEL OIL RECIRCULATION DMV	#6 BOILER/TRANSITION PIECE
IS THE SAMPLE HOMOGENEOUS?	NO	YES	YES
DOES IT CONTAIN LAYERS?	YES	NO	NO
IS THE SAMPLE FIBROUS?	YES	YES	YES
SAMPLE COLOR:	TAN/WHITE/GRAY	WHITE	TAN
SAMPLE CONTAIN ASBESTOS FIBERS?	YES	NO	NO
ASBESTOS TYPE AND PERCENT:	CHRYSOTILE 01 - 02		
TOTAL PERCENT ASBESTOS:	TOTAL: 1 - 2	0 PERCENT	0 PERCENT
FIBROUS MATERIALS AND PERCENT:	FIBROUS GLASS 70 - 80 CELLULOSE < 1%	FIBROUS GLASS 01 - 05 CELLULOSE 50 - 60	FIBROUS GLASS 30 - 40 CELLULOSE 05 - 10
NON-FIBROUS CONSTITUENTS:	BINDER, MATRIX, GLASS BEADS	BINDER	BINDER, GLASS BEADS
DEVIATION FROM TEST METHOD:	*1		

- THIS TEST REPORT RELATES ONLY TO THE ITEMS TESTED AND MUST NOT BE REPRODUCED EXCEPT WITH THE APPROVAL OF THE LABORATORY.
- ALL SAMPLES WILL BE DISPOSED OF 90 DAYS FOLLOWING SAMPLE RECEIPT UNLESS OTHERWISE INSTRUCTED BY THE CLIENT.
- UNDER CURRENT EPA REGULATIONS, AN "ASBESTOS CONTAINING MATERIAL" CONTAINS MORE THAN ONE PERCENT ASBESTOS.

*1 MATRIX OF SAMPLE DISSOLVED IN TETRAHYDROFURAN, HEATED, EVAPORATED, THEN ANALYSIS CONTINUES ACCORDING TO TEST METHOD

Union Carbide trial exhibit UC-1922: Alyce Hambleton to Belia Cortez Faxing Kevco Bulk Asbestos Sample Analysi... Published by AsbestosClaims.Law
ACL Doc 16981 · Page 3 of 11 asbestosclaims.law/library/16981/3

Kevco
LABORATORY & CONSULTING SERVICES

BULK ASBESTOS SAMPLE ANALYSIS REPORT

REPORT DATE: 5/14/90

TEST METHOD: 40 CFR CH. I (1-1-87 EDITION) PT 763, SUBPT. F APP. A. PAGES 293-299.

REPORT TO: UNION CARBIDE
P.O. BOX 186
PORT LAVACA TX 7,979
ATTENTION: CAL JONES

ANALYST SIGNATURE: Gary Landin
GARY LANDIN

KEVCO JOB NUMBER: DATE RECEIVED: DATE ANALYZED:	10402 5/14/90 5/14/90	10402 5/14/90 5/14/90	10402 5/14/90 5/14/90
CLIENT SAMPLE ID: PROJECT ID:	07	08	09
SAMPLE LOCATION:	ECONOMIZER	#4 BOILER VALVE/3RD LEVEL WESTSIDE	#4 BOILER/3RD LEVEL EAST SIDE
IS THE SAMPLE HOMOGENEOUS?	YES	NO	NO
DOES IT CONTAIN LAYERS?	NO	NO	NO
IS THE SAMPLE FIBROUS?	YES	YES	YES
SAMPLE COLOR:	WHITE	TAN	TAN
SAMPLE CONTAIN ASBESTOS FIBERS?	NO	YES	YES
ASBESTOS TYPE AND PERCENT:		CHRYSOTILE 05 - 15 AMOSITE 20 - 30	CHRYSOTILE 01 - 05 AMOSITE 40 - 50
TOTAL PERCENT ASBESTOS:	0 PERCENT	TOTAL: 25 - 45	TOTAL: 41 - 55
FIBROUS MATERIALS AND PERCENT:	FIBROUS GLASS 05 - 10 CELLULOSE 40 - 50	FIBROUS GLASS 20 - 30 CELLULOSE 01 - 02	FIBROUS GLASS 01 - 02 CELLULOSE 01 - 02
NONFIBROUS CONSTITUENTS:	BINDER	BINDER, FILLER	BINDER, FILLER
DEVIATION FROM TEST METHOD:		*2	*2

- THIS TEST REPORT RELATES ONLY TO THE ITEMS TESTED AND MUST NOT BE REPRODUCED EXCEPT WITH THE APPROVAL OF THE LABORATORY.
- ALL SAMPLES WILL BE DISPOSED OF 90 DAYS FOLLOWING SAMPLE RECEIPT UNLESS OTHERWISE INSTRUCTED BY THE CLIENT.
- UNDER CURRENT EPA REGULATIONS, AN "ASBESTOS CONTAINING MATERIAL" CONTAINS MORE THAN ONE PERCENT ASBESTOS.

*2 SAMPLE RECEIVED WET; SAMPLE DRIED PRIOR TO ANALYSIS

Union Carbide trial exhibit UC-1922: Alyce Hambleton to Belia Cortez Faxing Kevco Bulk Asbestos Sample Analysi... Published by AsbestosClaims.Law
ACL Doc 16981 · Page 4 of 11 asbestosclaims.law/library/16981/4

Kevco
LABORATORY & CONSULTING SERVICES

BULK ASBESTOS SAMPLE ANALYSIS REPORT

REPORT DATE: 5/14/90

TEST METHOD: 40 CFR CH. I (7-1-87 EDITION) PT 763. SUBPT. F APP. A. PAGES 293-299.

REPORT TO: UNION CARBIDE
P.O. BOX 186
PORT LAVACA TX 77979
ATTENTION: CAL JONES

ANALYST SIGNATURE: Gary Landini
GARY LANDINI

KEVCO JOB NUMBER: DATE RECEIVED: DATE ANALYZED:	10402 5/14/90 5/14/90	10402 5/14/90 5/14/90	10402 5/14/90 5/14/90
CLIENT SAMPLE ID: PROJECT ID:	10	11	12
SAMPLE LOCATION:	EVAPORATOR HEADER/ SOUTH	EVAPORATOR HEADER/ BY-PASS VALVE	#2 BOILER HEADER AT DMV
IS THE SAMPLE HOMOGENEOUS?	NO	NO	YES
DOES IT CONTAIN LAYERS?	NO	NO	NO
IS THE SAMPLE FIBROUS?	YES	YES	NO
SAMPLE COLOR:	TAN	WHITE/TAN	WHITE
SAMPLE CONTAIN ASBESTOS FIBERS?	YES	NO	NO
ASBESTOS TYPE AND PERCENT:	CHRYSOTILE 20 - 30 AMOSITE < 1%		
TOTAL PERCENT ASBESTOS:	TOTAL: 20 - 30	0 PERCENT	0 PERCENT
FIBROUS MATERIALS AND PERCENT:	FIBROUS GLASS 20 - 30 CELLULOSE 01 - 02	FIBROUS GLASS 30 - 40 CELLULOSE 05 - 10	FIBROUS GLASS 01 - 05 CELLULOSE 05 - 10
NONFIBROUS CONSTITUENTS:	BINDER, PERLITE	BINDER, FILLER, GLASS BEADS	BINDER, FILLER
DEVIATION FROM TEST METHOD:	*2	*1	

- THIS TEST REPORT RELATES ONLY TO THE ITEMS TESTED AND MUST NOT BE REPRODUCED EXCEPT WITH THE APPROVAL OF THE LABORATORY.
- ALL SAMPLES WILL BE DISPOSED OF 90 DAYS FOLLOWING SAMPLE RECEIPT UNLESS OTHERWISE INSTRUCTED BY THE CLIENT.
- UNDER CURRENT EPA REGULATIONS, AN "ASBESTOS CONTAINING MATERIAL" CONTAINS MORE THAN ONE PERCENT ASBESTOS.

*2 SAMPLE RECEIVED WET: SAMPLE DRIED PRIOR TO ANALYSIS
*1 MATRIX OF SAMPLE DISSOLVED IN TETRAHYDROFURAN, HEATED, EVAPORATED, THEN ANALYSIS CONTINUES ACCORDING TO TEST METHOD

Union Carbide trial exhibit UC-1922: Alyce Hambleton to Belia Cortez Faxing Kevco Bulk Asbestos Sample Analysi... Published by AsbestosClaims.Law
ACL Doc 16981 · Page 5 of 11 asbestosclaims.law/library/16981/5

Kevco
LABORATORY & CONSULTING SERVICES

BULK ASBESTOS SAMPLE ANALYSIS REPORT

REPORT DATE: 5/14/90

TEST METHOD: 40 CFR CH. I (7 1 87 EDITION), #1 763, SUBPT. F APP A. PAGES 397-399.

REPORT TO: UNION CARBIDE
P.O. BOX 186
PORT LAVACA TX 77979
ATTENTION: CAL JONES

ANALYST SIGNATURE: M Saulsbury
MARIANNE SAULSBURY

KEVCO JOB NUMBER: DATE RECEIVED: DATE ANALYZED:	10402 5/14/90 5/14/90	10402 5/14/90 5/14/90	10402 5/14/90 5/14/90
CLIENT SAMPLE ID: PROJECT ID:	14	15	16
SAMPLE LOCATION:	#1 EVAPORATOR	#1 ID FAN	#1 BOILER EXHAUST/ OFF VALVE TO O2
IS THE SAMPLE HOMOGENEOUS?	YES	YES	YES
DOES IT CONTAIN LAYERS?	NO	NO	NO
IS THE SAMPLE FIBROUS?	YES	YES	YES
SAMPLE COLOR:	WHITE	GRAY	GRAY
SAMPLE CONTAIN ASBESTOS FIBERS?	NO	YES	YES
ASBESTOS TYPE AND PERCENT:		CHRYSOTILE 40 - 50 AMOSITE 10 - 20	CHRYSOTILE < 1%
TOTAL PERCENT ASBESTOS:	0 PERCENT	TOTAL: 50 - 70	LESS THAN 1 PERCENT
FIBROUS MATERIALS AND PERCENT:	FIBROUS GLASS 01 - 05 CELLULOSE 40 - 50		FIBROUS GLASS 20 - 30 CELLULOSE 01 - 05 HAIR (WOOL) 01 - 05
NONFIBROUS CONSTITUENTS:	BINDER	BINDER	BINDER
DEVIATION FROM TEST METHOD:	*2		

- THIS TEST REPORT RELATES ONLY TO THE ITEMS TESTED AND MUST NOT BE REPRODUCED EXCEPT WITH THE APPROVAL OF THE LABORATORY.
- ALL SAMPLES WILL BE DISPOSED OF 90 DAYS FOLLOWING SAMPLE RECEIPT UNLESS OTHERWISE INSTRUCTED BY THE CLIENT.
- UNDER CURRENT EPA REGULATIONS, AN "ASBESTOS CONTAINING MATERIAL" CONTAINS MORE THAN ONE PERCENT ASBESTOS.

*2 SAMPLE RECEIVED WET; SAMPLE DRIED PRIOR TO ANALYSIS

Union Carbide trial exhibit UC-1922: Alyce Hambleton to Belia Cortez Faxing Kevco Bulk Asbestos Sample Analysi... Published by AsbestosClaims.Law
ACL Doc 16981 · Page 6 of 11 asbestosclaims.law/library/16981/6

Kevco
LABORATORY & CONSULTING SERVICES

BULK ASBESTOS SAMPLE ANALYSIS REPORT

REPORT DATE: 5/14/90

TEST METHOD: 40 CFR CH. I (1-1-87 EDITION) PT 763, SUBPT. F APP. A. PAGES 293-299.

REPORT TO: UNION CARBIDE
P.O. BOX 186
PORT LAVACA TX 77979
ATTENTION: CAL JONES

ANALYST SIGNATURE: M Saulsbury
MARIANNE SAULSBURY

KEVCO JOB NUMBER: DATE RECEIVED: DATE ANALYZED:	10402 5/14/90 5/14/90	10402 5/14/90 5/14/90	10402 5/14/90 5/14/90
CLIENT SAMPLE ID: PROJECT ID:	17	18	19
SAMPLE LOCATION:	BOILER CONTROL ROOM	AT EVAPORATOR ASB. IN MATRIX MAT.	LINES NORTH OF SERVICE WATER TANK
IS THE SAMPLE HOMOGENEOUS?	NO	NO	YES
DOES IT CONTAIN LAYERS?	NO	YES	NO
IS THE SAMPLE FIBROUS?	YES	YES	YES
SAMPLE COLOR:	TAN/GRAY	GRAY	BROWN
SAMPLE CONTAIN ASBESTOS FIBERS?	NO	YES	NO
ASBESTOS TYPE AND PERCENT:		CHRYSOTILE 01 - 02	
TOTAL PERCENT ASBESTOS:	0 PERCENT	TOTAL 1 - 2	0 PERCENT
FIBROUS MATERIALS AND PERCENT:	FIBROUS GLASS 05 - 10 CELLULOSE 05 - 10	FIBROUS GLASS 05 - 10 CELLULOSE 30 - 40	FIBROUS GLASS 30 - 40
NONFIBROUS CONSTITUENTS:	PERLITE	BINDER	PERLITE
DEVIATION FROM TEST METHOD:			

- THIS TEST REPORT RELATES ONLY TO THE ITEMS TESTED AND MUST NOT BE REPRODUCED EXCEPT WITH THE APPROVAL OF THE LABORATORY.
- ALL SAMPLES WILL BE DISPOSED OF 90 DAYS FOLLOWING SAMPLE RECEIPT UNLESS OTHERWISE INSTRUCTED BY THE CLIENT.
- UNDER CURRENT EPA REGULATIONS, AN "ASBESTOS CONTAINING MATERIAL" CONTAINS MORE THAN ONE PERCENT ASBESTOS.

Kevco SERVICES INC. · 856 PITTSBURGH ROAD · BUTLER, PA [illegible]
TEL 412-586-0313 FAX 412-586-2172

BRD 1300

Kevco
LABORATORY & CONSULTING SERVICES

BULK ASBESTOS SAMPLE ANALYSIS REPORT

REPORT DATE: 5/14/90

TEST METHOD: 40 CFR CH. I (1-1-87 EDITION) PT 763, SUBPT. F APP. A, PAGES 293-299.

REPORT TO: UNION CARBIDE
P.O. BOX 184
PORT LAVACA TX 77979
ATTENTION: CAL JONES

ANALYST SIGNATURE: M. Saulsbury
MARIANNE SAULSBURY

KEVCO JOB NUMBER: DATE RECEIVED: DATE ANALYZED:	10402 5/14/90 5/14/90	10402 5/14/90 5/14/90	10402 5/14/90 5/14/90
CLIENT SAMPLE ID: PROJECT ID:	20	21	22
SAMPLE LOCATION:	#3 BOILER/VALVE INSULATION	#1 BOILER ID FAN	#2 CONDENSATE PUMP
IS THE SAMPLE HOMOGENEOUS?	YES	YES	YES
DOES IT CONTAIN LAYERS?	NO	NO	NO
IS THE SAMPLE FIBROUS?	YES	YES	YES
SAMPLE COLOR:	WHITE	TAN	WHITE
SAMPLE CONTAIN ASBESTOS FIBERS?	YES	YES	YES
ASBESTOS TYPE AND PERCENT:	AMOSITE 50 - 60	CHRYSOTILE 05 - 10 AMOSITE 40 - 50	CHRYSOTILE 05 - 10 AMOSITE 50 60
TOTAL PERCENT ASBESTOS:	TOTAL: 50 - 60	TOTAL: 45 - 60	TOTAL: 55 - 70
FIBROUS MATERIALS AND PERCENT:			
NONFIBROUS CONSTITUENTS:	BINDER	BINDER	BINDER
DEVIATION FROM TEST METHOD:			

- THIS TEST REPORT RELATES ONLY TO THE ITEMS TESTED AND MUST NOT BE REPRODUCED EXCEPT WITH THE APPROVAL OF THE LABORATORY.
- ALL SAMPLES WILL BE DISPOSED OF 90 DAYS FOLLOWING SAMPLE RECEIPT UNLESS OTHERWISE INSTRUCTED BY THE CLIENT.
- UNDER CURRENT EPA REGULATIONS, AN "ASBESTOS CONTAINING MATERIAL" CONTAINS MORE THAN ONE PERCENT ASBESTOS.

Kevco
LABORATORY & CONSULTING SERVICES

BULK ASBESTOS SAMPLE ANALYSIS REPORT

REPORT DATE: 5/14/90

TEST METHOD: 40 CFR CH. I (1-1-87 EDITION) PT 763, SUBPT. F APP. A. PAGES 293-299.

REPORT TO: UNION CARBIDE
P.O. BOX 166
PORT LAVACA TX 77979
ATTENTION: CAL JONES

ANALYST SIGNATURE: M Saulsbury
MARIANNE SAULSBURY

KEVCO JOB NUMBER: DATE RECEIVED: DATE ANALYZED:	10402 5/11/90 5/12/90	10402 5/11/90 5/14/90	10402 5/11/90 5/14/90
CLIENT SAMPLE ID: PROJECT ID:	23	24	25
SAMPLE LOCATION:	#1 D.A. PUMPS 200W STEAM INLET	#2 GENERATOR ASB. IN MATRIX ONLY	SPOT #2 TC LOAD RACK
IS THE SAMPLE HOMOGENEOUS?	YES	YES	YES
DOES IT CONTAIN LAYERS?	NO	NO	NO
IS THE SAMPLE FIBROUS?	YES	YES	YES
SAMPLE COLOR:	BROWN	WHITE	WHITE
SAMPLE CONTAIN ASBESTOS FIBERS?	NO	YES	NO
ASBESTOS TYPE AND PERCENT:		CHRYSOTILE 01 - 02	
TOTAL PERCENT ASBESTOS:	0 PERCENT	TOTAL: 1 - 2	0 PERCENT
FIBROUS MATERIALS AND PERCENT:	FIBROUS GLASS 10 - 20	FIBROUS GLASS 05 - 10 CELLULOSE 20 - 30 HAIR (WOOL) 10 - 20	CELLULOSE 01 - 02 HAIR (WOOL) 01 - 05
NONFIBROUS CONSTITUENTS:	PERLITE	MATRIX	MATRIX
DEVIATION FROM TEST METHOD:			

- THIS TEST REPORT RELATES ONLY TO THE ITEMS TESTED AND MUST NOT BE REPRODUCED EXCEPT WITH THE APPROVAL OF THE LABORATORY.
- ALL SAMPLES WILL BE DISPOSED OF 90 DAYS FOLLOWING SAMPLE RECEIPT UNLESS OTHERWISE INSTRUCTED BY THE CLIENT.
- UNDER CURRENT EPA REGULATIONS, AN "ASBESTOS CONTAINING MATERIAL" CONTAINS MORE THAN ONE PERCENT ASBESTOS.

Union Carbide trial exhibit UC-1922: Alyce Hambleton to Belia Cortez Faxing Kevco Bulk Asbestos Sample Analysi... Published by AsbestosClaims.Law
ACL Doc 16981 · Page 9 of 11 asbestosclaims.law/library/16981/9

Kevco

LABORATORY & CONSULTING SERVICES

BULK ASBESTOS SAMPLE ANALYSIS REPORT

REPORT DATE: 5/14/90

TEST METHOD: 40 CFR CH. I (1-1-87 EDITION) PT 763, SUBPT. F APP. A. PAGES 293-299.

REPORT TO: UNION CARBIDE
P.O. BOX 186
PORT LAVACA TX 77979
ATTENTION: CAL JONES

ANALYST SIGNATURE: M Saulsbury
MARIANNE SAULSBURY

KEVCO JOB NUMBER: DATE RECEIVED: DATE ANALYZED:	10602 5/14/90 5/14/90		
CLIENT SAMPLE ID: PROJECT ID:	26		
SAMPLE LOCATION:	40# STEAM LINES Part		
IS THE SAMPLE HOMOGENEOUS?	YES		
DOES IT CONTAIN LAYERS?	NO		
IS THE SAMPLE FIBROUS?	YES		
SAMPLE COLOR:	PINK		
SAMPLE CONTAIN ASBESTOS FIBERS?	NO		
ASBESTOS TYPE AND PERCENT:			
TOTAL PERCENT ASBESTOS:	0 PERCENT		
FIBROUS MATERIALS AND PERCENT:	FIBROUS GLASS 01 - 02 CELLULOSE 01 - 02		
NONFIBROUS CONSTITUENTS:	MATRIX		
DEVIATION FROM TEST METHOD:			

- THIS TEST REPORT RELATES ONLY TO THE ITEMS TESTED AND MUST NOT BE REPRODUCED EXCEPT WITH THE APPROVAL OF THE LABORATORY.
- ALL SAMPLES WILL BE DISPOSED OF 90 DAYS FOLLOWING SAMPLE RECEIPT UNLESS OTHERWISE INSTRUCTED BY THE CLIENT.
- UNDER CURRENT EPA REGULATIONS, ANY "ASBESTOS CONTAINING MATERIALS" CONTAINS MORE THAN ONE PERCENT ASBESTOS.

Kevco
LABORATORY & CONSULTING SERVICES

BULK ASBESTOS SAMPLE ANALYSIS REPORT

REPORT DATE: 5/14/90

TEST METHOD: 40 CFR CH. I (7-1-87 EDITION) PT 763, SUBPT. F APP. A. PAGES 293-299.

REPORT TO: UNION CARB
P.O. BOX 186
PORT LAVACA TX 77979
ATTENTION: CAL JONES

ANALYST SIGNATURE: Gary Landtrip
GARY LANDTRIP

KEVCO JOB NUMBER: DATE RECEIVED: DATE ANALYZED:	10402 5/14/90 5/14/90		
CLIENT SAMPLE ID: PROJECT ID:	13		
SAMPLE LOCATION:	#2 BOILER HEADER AT 90 DEGREES		
IS THE SAMPLE HOMOGENEOUS?	YES		
[illegible]	NO		
IS THE SAMPLE FIBROUS?	NO		
SAMPLE COLOR:	WHITE		
SAMPLE CONTAIN ASBESTOS FIBERS?	NO		
ASBESTOS TYPE AND PERCENT:			
TOTAL PERCENT ASBESTOS:	0 PERCENT		
FIBROUS MATERIALS AND PERCENT:	FIBROUS GLASS 10 - 20 CELLULOSE 01 - 05		
NONFIBROUS CONSTITUENTS:	BINDER , FILLER		
DEVIATION FROM TEST METHOD:	#2		

THIS TEST REPORT RELATES ONLY TO THE ITEMS TESTED AND MUST NOT BE REPRODUCED EXCEPT WITH THE APPROVAL OF THE LABORATORY.

- ALL SAMPLES WILL BE DISPOSED OF 90 DAYS FOLLOWING SAMPLE RECEIPT UNLESS OTHERWISE INSTRUCTED BY THE CLIENT.
- UNDER CURRENT EPA REGULATIONS, AN "ASBESTOS CONTAINING MATERIAL" CONTAINS MORE THAN ONE PERCENT ASBESTOS

** SAMPLES RECEIVED WET; DOUBLE DRIED PRIOR TO ANALYSIS

Kevco SERVICES INC • 890 PITTSBURGH ROAD • BUTLER, PA 16001
TEL 412-586-6333 FAX 412 586-2172

Union Carbide trial exhibit UC-1922: Alyce Hambleton to Belia Cortez Faxing Kevco Bulk Asbestos Sample Analys... Published by AsbestosClaims.Law
ACL Doc 16981 · Page 11 of 11 asbestosclaims.law/library/16981/11