RAYMOND GAMBINO, M.D.
PAUL A. KRIEGER, M.D.
JOSEPH E. O'BRIEN, M.D.

WU-0191 #58

INSIDE SIDE # 1	E0639	NOT GIVEN	03/24/86	04/03/86
	CLIENT	DATE DRAWN	DATE REC'D	DATE OF REPORT
	MB	UNION CARBIDE/CHARLESTON WT YB-03/512-837505-4 P.O. BOX 8004 ST. CHARLESTON WV 25303		87383 E09256

TEST NAME	RESULT	UNITS	REFERENCE RANGE

********** SPECIAL REPORT **********

ENVIRONMENTAL SAMPLE

PLAINTIFF'S EXHIBIT
UC-2298

TLC REQUESTED ASBESTOS BY POLARIZED LIGHT MICROSCOPY

CLIENT SAMPLE ID: INSIDE CORE - CEILING WELDING SHOP

DOES SAMPLE CONTAIN ASBESTOS FIBERS: NO

FIBROUS ASBESTOS TYPE (IN PERCENT):

CHRYSOTILE =	ND	TREMOLITE =	ND
AMOSITE (GRUNERITE) =	ND	ACTINOLITE =	ND
ANTHOPHYLLITE =	ND	CROCIDOLITE =	ND

TOTAL PERCENT FIBROUS ASBESTOS IN SAMPLE = ND

OTHER FIBROUS MATERIALS PRESENT (IN PERCENT) = CELLULOSE 5
FIBERGLASS 10

NON-FIBROUS MATERIALS PRESENT = GYPSUM BOARD?, WOLLASTONITE CALCITE

Copyright (c) by MetPath Inc. All rights reserved

Union Carbide trial exhibit UC-2298: MetPath and Corning Asbestos Test Reports on Ceiling Samples from Union C...
Published by AsbestosClaims.Law
ACL Doc 17290 · Page 1 of 3
asbestosclaims.law/library/17290/1

MetPath

CENTRAL LABORATORY FACILITY
ONE MALCOLM AVE.
TETERBORO, NEW JERSEY 07608
CLIENT SERVICE 800-[illegible] 800-[illegible]

RAYMOND GAMBINO M.D
PAUL A. KRIEGER, M.D.
JOSEPH E. O'BRIEN, M.D

WV-0191
#57

NO. 2	E0653NOT GIVEN	04/16/86	04/25/86
PATIENT	DATE DRAWN	DATE RECD	DATE OF REPORT
MB			87383
SEX	AGE		ACCT NO
			E09497
PATIENT SOCIAL SEC. NO.			SPEC NO

UNION CARBIDE/CHARLESTON
WC YOUNG/512-837505-4
P.O. BOX 8004
SO CHARLESTON WV 25303

TEST NAME	RESULT	UNITS	REFERENCE RANGE

********** SPECIAL REPORT **********

ENVIRONMENTAL SAMPLE

TEST REQUESTED ASBESTOS BY POLARIZED LIGHT MICROSCOPY

CLIENT SAMPLE ID BULK SAMPLE 2 Bldg 157 Lunch Room Ceiling Tile

DOES SAMPLE CONTAIN ABESTOS FIBERS NONE DETECTED

FIBROUS ASBESTOS TYPE (IN PERCENT)=

CHRYSOTILE =	ND	TREMOLITE =	ND
AMOSITE (GRUNERITE) =	ND	ACTINOLITE =	ND
ANTHOPHYLLITE =	ND	CROCIDOLATE =	ND

TOTAL PERCENT FIBROUS ASBESTOS IN SAMPLE = NONE DETECTED

OTHER FIBROUS MATERIALS PRESENT (PERCENT)= MINERAL WOOD 4
CELLULOSE 8
NYLON LT-1

NONFIBROUS MATERIALS PRESENT =GYPSUM/QUARTZ/PERLITE/PAINT( )

[illegible] 1983 by MetPath Inc. All rights reserved

Union Carbide trial exhibit UC-2298: MetPath and Corning Asbestos Test Reports on Ceiling Samples from Union C... Published by AsbestosClaims.Law
ACL Doc 17290 · Page 2 of 3 asbestosclaims.law/library/17290/2

Okay, I didn't you request that this be checked? JKC

CORNING ENGINEERING ENVIRONMENTAL SERVICES REPORT

RECEIVED
JUN 11 1986
MAINTENANCE DEPT

CEES Client No.: 43455-051

Date Reported: May 29, 1986

Sample Description: Bulk Sample 2 WOMEN'S LOCKER ROOM CEILING Bl. 308

Specimen Number: E09980

Lab I.D. No.: F860527.04

Test Description: Analysis of Asbestos in Insulation by Polarized Light Microscopy with Dispersion Staining.

GROSS APPEARANCE:	Is sample homogeneous?	Yes
	Is sample fibrous?	Yes
	Other Observations:	Tan Colored Tile
DOES SAMPLE CONTAIN ASBESTOS FIBERS?		Not Detected
FIBROUS ASBESTOS TYPE: (in %)	Chrysotile -	Not Detected
	Amosite -	Not Detected
	Anthophyllite -	Not Detected
	Tremolite -	Not Detected
	Actinolite -	Not Detected
	Crocidolite -	Not Detected
TOTAL PERCENT FIBROUS ASBESTOS IN SAMPLE:		Not Detected
OTHER FIBROUS MATERIALS PRESENT: (in %)		Nonconiferous Wood - 100%
NONFIBROUS MATERIALS PRESENT:		None Detected

JKC -

I didn't ask for this sample, but for the Bldg 308 upstairs ceiling tile.

J.D. 6/11

rmation is to be used only for account 43455.

UCC 002547