PLAINTIFF'S EXHIBIT

UC-2406

APPENDIX II

TEST DATA

ATMOSPHERIC DUST CONCENTRATION DATA

	Experimental Pan Cast 4-in. Blocks			Std. 4-in. Tachydrometer	Std. 4-in.
	1-AT	2-AT	3-AT*	4-AT	5-AT
Concentration in mppcf of air					
Dried at 250F	110.8	19.9	16.4	34.2	52.0
Conditioned at 70% RH, 70F	59.3	14.8	47.1	15.8	36.4
Conditioned at 95-100% RH, 95F	89.6	20.6	31.4	104.0	97.6
Avg. of three conditions	83.2	18.1	31.6	51.3	62.0
Moisture Absorbed During Conditioning - %					
Dry to 70% RH, 70F	2.7	2.0	2.5	3.6	3.9
Dry to 95-100% RH, 95F	13.6	12.3	17.2	15.6	12.8

*This formulation was used for samples submitted to Union Carbide for evaluation. Refer to formula No. 58, samples 21, 22, 23, Research Report No. [illegible], p 1.

Bh. Peale

UCC 015607

Union Carbide trial exhibit UC-2406: Appendix II Test Data: Atmospheric Dust Concentration Data for Pan Cast Blo... Published by AsbestosClaims.Law
ACL Doc 17385 · Page 1 of 1 asbestosclaims.law/library/17385/1