
PLAINTIFF'S EXHIBIT

UC-3043

F 71-100



UCC 001748

PERFORMANCE OF *CALIDRIA* R-G 144 AND COMPETITIVE THIXOTROPES

in Liquid Epoxy Resin Systems

CALIDRIA R-G 144 Asbestos is a highly purified fiber product that is an effective, low-cost thickening agent and thixotrope for epoxy resin systems. Produced by UNION CARBIDE's proprietary process, an unusually high fiber content is obtained, that is both grit-free and non-abrasive.

Comparative evaluations have shown that up to 50 per cent less CALIDRIA R-G 144 Asbestos is required than other commonly used thickeners, to provide equivalent viscosity and thixotropic properties, in liquid epoxy resin systems. Because CALIDRIA Asbestos is much lower in price, its cost-performance is outstanding.

Figures 1 and 2 compare the relative differences in viscosity and thixotropy of BAKELITE Epoxy Resin ERL-2774 solutions containing equivalent concentrations of CALIDRIA R-G 144 Asbestos, micro-crystalline silicate, and pyrogenic silica.

The superiority of CALIDRIA R-G 144 is again indicated, as shown in Figures 1 and 2, in that its use does not require amine-type additives usually recommended with the use of pyrogenic silicas.

Figures 3 and 4 show the superior performance of CALIDRIA R-G 144 Asbestos in BAKELITE Resin Hardener ZZL-0814, in comparison with equivalent mixtures of micro-crystalline silicate and pyrogenic silica.

RESIN AND AMINE HARDENER EVALUATION

In preparing test samples used in determining data for the following graphs, the thixotropes were added to the liquid resin or hardener at 25°C. and dispersed in a "Cowles" Dissolver at 2400 rpm. for 5 minutes.

VISCOSITY MEASUREMENTS

Viscosities of the prepared test samples were measured on a Brookfield Model RVF Viscometer at 2 and 20 rpm.

IMPORTANT: This information is not to be taken as a warranty or representation for which we assume legal responsibility nor as permission or recommendation to practice any patented invention without a license. It is offered solely for your consideration, investigation, and verification.

Union Carbide trial exhibit UC-3043: Union Carbide Calidria Asbestos Brochure: Performance of Calidria R-G 144 a... Published by AsbestosClaims.Law


ACL Doc 17887 · Page 2 of 4 asbestosclaims.law/library/17887/2


PERFORMANCE OF *CALIDRIA* R-G 144 AND COMPETITIVE THIXOTROPES

in Liquid Epoxy Resin Systems

FIGURES 1 AND 2


COMPARISON OF VISCOSITY AND THIXOTROPY OF BAKELITE® EPOXY RESIN ERL-2774 SOLUTIONS CONTAINING EQUIVALENT CONCENTRATIONS OF *CALIDRIA* R-G 144 ASBESTOS, MICRO-CRYSTALLINE SILICATE, AND PYROGENIC SILICA






FIGURES 3 AND 4

PERFORMANCE OF *CALIDRIA* R-G 144 ASBESTOS IN BAKELITE® RESIN HARDENER ZZL-0814 COMPARED WITH EQUIVALENT MIXTURES OF MICRO-CRYSTALLINE SILICATE AND PYROGENIC SILICA





UCC 001750

Union Carbide trial exhibit UC-3043: Union Carbide Calidria Asbestos Brochure: Performance of Calidria R-G 144 a... Published by AsbestosClaims.Law
ACL Doc 17887 · Page 3 of 4 asbestosclaims.law/library/17887/3

Any of our offices below will be glad to give you complete information on properties, applications, and prices of "Calidria" asbestos.

Calidria ASBESTOS

Marketing and Technical Center

Niagara Falls, New York 14302	P. O. Box 579	716-285-3311

Plant

King City, California 93930	P. O. Box K	408-385-5961

Sales Offices

Atlanta, Georgia 30329	17 Executive Park Dr.	404-633-6161
Baltimore, Maryland 21207	Beltway Bldg. 6707 Whitestone Rd.	301-944-8211
Boston, Massachusetts 02194	300 First Ave., Needham Heights	617-444-5400
Buffalo, New York 14225	3343 Harlem Rd.	716-837-6450
Charlotte, North Carolina 28210	6230 Fairview Rd.	704-364-1400
Chicago, Illinois 60606	120 South Riverside Plaza	312-822-7000
Cincinnati, Ohio 45227	West Street and Madisonville Rd.	513-272-0206
Cleveland, Ohio 44114	1300 Lakeside Ave., N.E.	216-621-4202
Clifton, New Jersey 07012	935 Allwood Rd.	201-778-2900
Dallas, Texas 75207	2710 Stemmons Freeway	214-631-0010
Detroit (Southfield, Michigan Sales Office)		313-354-0800
Houston, Texas 77027	3737 Greenway Plaza Dr.	713-621-1000
Indianapolis (Cincinnati, Ohio Sales Office)		317-255-3181
Kansas City (St. Louis, Mo. Sales Office)		913-362-2200
Los Angeles, California 90058	2770 Leonis Blvd.	213-583-3061
Memphis (Atlanta, Ga. Sales Office)		901-396-5375
Minneapolis, Minnesota 55416	3033 Excelsior Blvd.	612-927-4221
Moorestown, New Jersey 08057	Route 38 and Pleasant Valley Rd.	609-235-6200
New York, New York 10017	270 Park Ave.	212-551-3763
Philadelphia (Moorestown, New Jersey Sales Office)		215-923-3200
Pittsburgh, Pennsylvania 15220	P'kway Center, 875 Greentree Rd.	412-922-5700
Southfield, Michigan 48075	26500 Northwestern Highway	313-354-0800
St. Louis, Missouri 63105	10 South Brentwood Blvd.	314-726-0324
San Francisco, California 94111	One California St.	415-765-1244
Seattle, Washington 96118	4726 Rainier Ave., South	206-723-8660

UNION CARBIDE

THE DISCOVERY COMPANY

UNION CARBIDE CORPORATION
MINING AND METALS DIVISION
270 PARK AVENUE, NEW YORK, N. Y. 10017

F-71-100
7/71-4M

"Bakelite," "Calidria," and "Union Carbide" are registered trade marks of Union Carbide Corporation.

Printed in U.S.A.

UCC 001751