PLAINTIFF'S EXHIBIT

UC-3183

CALIDRIA ASBESTOS RG-244

TYPICAL CHEMICAL ANALYSIS

Component	Weight %
MgO	38.2
SiO_2	46.1
Al_2O_3	0.2
Fe	1.4
Ca	0.025
Cd	<0.00002
Co	0.004
Cr	0.13
Cu	0.005
Mn	0.05
Ni	0.16
Se	<0.001
Loss on Ignition (CO_2 & H_2O)	12.7

A-9703

TYPICAL SPECTROGRAPHIC ANALYSIS

Component	Detection Limit, Wt. %	Analysis, Wt. %
Ag	0.001	N.D.(2)
Al	0.003	0.08-0.8
As	0.01	N.D.
Au	0.002	N.D.
B	0.006	N.D.
Ba	0.003	N.D.
Be	0.001	N.D.
Bi	0.005	N.D.
Ca	0.002	0.008-0.08
Cb	0.006	N.D.
Cd	---	<0.00002(3)
Co	0.01	0.004-0.04
Cr	0.003	0.02-0.2
Cs	N.A.(1)	----
Cu	0.001	N.D.
Fe	0.006	0.4-4.0
Ga	0.01	N.D.
Ge	0.005	N.D.
Hf	0.03	N.D.
Hg	0.02	N.D.
In	0.03	N.D.
Ir	0.03	N.D.
K	N.A.(1)	----
La	0.01	N.D.
Li	0.1	N.D.
Mg	0.001	Major
Mn	0.003	0.008-0.08
Mo	0.003	N.D.
Na	0.03	0.08-0.8
Ni	0.003	0.08-0.8
Os	0.03	N.D.
P	0.08	N.D.
Pb	0.003	N.D.
Pd	0.005	N.D.
Pt	0.005	N.D.
Rb	N.A.(1)	----
Re	0.03	N.D.
Rh	0.02	N.D.
Ra	0.03	N.D.
Sb	0.01	N.D.
Sc	0.01	N.D.
Se	----	<0.001(3)
Si	0.001	Major
Sn	0.002	N.D.
Sr	0.01	N.D.
Ta	0.01	N.D.
Te	0.05	N.D.
Th	0.03	N.D.
Ti	0.003	0.0008-0.008
Tl	0.2	N.D.
U	0.1	N.D.
V	0.003	N.D.
W	0.01	N.D.
Y	0.01	N.D.
Yb	0.01	N.D.
Zn	0.02	N.D.
Zr	0.006	N.D.

(1) N.A. - Not analyzed.

(2) N.D. - Not detected.

(3) By chemical analysis.

UCC 016442

Union Carbide trial exhibit UC-3183: Calidria Asbestos RG-244 Typical Chemical and Spectrographic Analysis (und... Published by AsbestosClaims.Law
ACL Doc 18010 · Page 1 of 1 asbestosclaims.law/library/18010/1