PLAINTIFF'S EXHIBIT

UC-3380

ATI

ASBESTOS TESTING INC.

5205 NOYES AVE. • CHARLESTON, WV 25304 • (304) 925-6795 October 23, 1986

Erik A. Osby
Industrial Hygiene Dept.
Union Carbide Corporation
P.O. Box 2831
Charleston, WV 25330

The following bulk insulation analysis results pertain to samples received on 10/21/86. All bulk insulation analysis is performed in accordance with EPA recommendations concerning analysis of bulk insulation using Polarized Light Microscopy.

ANALYSIS RESULTS

Sample #1	N.D.-Asbestos 1%-Mineral Wool 5%-Cellulose 94%-Clay
Sample #2	N.D.-Asbestos 1%-Mineral Wool 99%-Foam Glass
Sample #3	5%-Asbestos (Chrysotile) 10%-Cellulose 85%-Foam Glass
Sample #4	85%-Asbestos (5%-Amosite) (80%-Chrysotile) 15%-Clay
Sample #5	40%-Asbestos (10%-Amosite) (30%-Chrysotile) 60%-Clay
Sample #6	15%-Asbestos (Amosite) 85%-Clay

Respectfully submitted,

John S. Ferrell
Industrial Hygienist

AU4002

UCC 008985