PLAINTIFF'S EXHIBIT

UC-3972

UNION CARBIDE

Calidria ASBESTOS

UNION CARBIDE CORPORATION · METALS DIVISION · P. O. BOX 579 · NIAGARA FALLS, N.Y. 14302 · TEL: 716-278-3376

A07879

SUGGESTED EXTERIOR WHITE HI-BUILD FLEXIBLE COATING

3JG-124B

	LBS.	GALS.
CHARGE INTO MIXER UNDER SLOW AGITATION:		
Water	150.0	18.0
CELLOSIZE QP-4400	4.0	0.4
Dowicil 75	2.0	0.2
Colloid 677	2.5	0.3
Tamol 731	4.0	0.4
Ethylene Glycol	20.0	2.2
Ti Pure R960	60.0	1.8
UCAR Latex 153	100.0	11.2
ASP 400	75.0	3.4
Nopcocide N-96	5.0	0.3
Duramite	75.0	3.3
Colloid 677	2.0	0.2
Vermiculite or Pumice #3	34.0	1.7
Disperse 10 min. at moderate Speed, then add following at Slow Speed:		
CALIDRIA HPO or SG-210 Fibers	10.0	0.4
UCAR Latex 153	319.0	35.7
UCAR Latex 365	181.0	20.0
Mineral Spirits	3.0	0.5
	1046.5	100.0

PHYSICAL CHARACTERISTICS

PVC	23.8%	Contrast Ratio	0.95 (3.5 mil dry film)
Total Solids by Wt.	57.2%	Brightness	86%
Viscosity	105-115 KU	pH	7.2

Application - Brush or Hopper-Loaded Texture Coating Spray Gun

UCC 015023

Published by AsbestosClaims.Law
asbestosclaims.law/library/18602/2