Calidria ASBESTOS

UNION CARBIDE CORPORATION · METALS DIVISION · P. O. BOX 579 · NIAGARA FALLS, N.Y. 14302 · TEL: 716-278-3376

PLAINTIFF'S EXHIBIT


UC-4113

TYPICAL PRODUCT CHARACTERISTICS FOR HIGH PURITY OPEN (HPO)

PROPERTY	TYPICAL VALUE
Moisture Content, %	2
Magnetite, %	0.75
+65 Mesh, Wet Screen %	1.0
pH	9.5
Specific Gravity	2.45
Surface Area, m^2/gm	60
Refractive Index, n_d 25°C	1.54-1.56
Reflectance, GE Brightness, %	74
Nature of Surface Charge	Electropositive (Cationic)
Bulking Value, gal./100 lbs.	4.8
Aspect Ratio (Average L/D)	200:1
Shipping Density, lbs/ft^3	17

Single Bag Weight	35 lbs.
Single Pallet Weight, 40 bags	1,575 lbs.
27' Truck Load, 17 pallets	26,775 lbs.
50' Railcar Load, 52 pallets	81,900 lbs.

X412779



Published by AsbestosClaims.Law
asbestosclaims.law/library/18720/2

Published by AsbestosClaims.Law
asbestosclaims.law/library/18720/3