UNION CARBIDE

Calidria ASBESTOS

UNION CARBIDE CORPORATION • METALS DIVISION • P. O. BOX 579 • NIAGARA FALLS, N.Y. 14302 • TEL: 716-278-3376

PLAINTIFF'S EXHIBIT

UC-4114

TYPICAL PRODUCT CHARACTERISTICS FOR HIGH PURITY PELLETS (HPP)

PROPERTY	TYPICAL VALUE
Moisture Content, %	2
Magnetite, %	0. 75
+65 Mesh, Wet Screen % (after repulping)	1. 0
pH	9. 5
Specific Gravity	2. 45
Surface Area of Fibrous Product, m^2/gm	60
Refractive Index, n_d 25 °C	1. 54-1. 56
Reflectance, GE Brightness, %	74
Nature of Surface Charge	Electropositive (Cationic)
Bulking Value, gal. /100 lbs.	4. 8
Aspect Ratio of Fibers (Average L/D)	200/1
Shipping Density, lbs. $/ft^3$	40

Single Bag Weight	50 lbs.
Single Pallet Weight, 40 bags	2, 000 lbs.
27' Truck Load, 10 pallets	20, 000 lbs.
50' Railcar Load, 60 pallets	120, 000 lbs.

X412781

"Typical Product Characteristics (HPP) 52A

X412780

PLAINTIFF'S EXHIBIT

UC-551

Published by AsbestosClaims.Law
asbestosclaims.law/library/18721/2

Published by AsbestosClaims.Law
asbestosclaims.law/library/18721/3