UNION CARBIDE CORPORATION · METALS DIVISION · P. O. BOX 579 · NIAGARA FALLS, N.Y. 14302 · TEL: 716-278-3376

TYPICAL PRODUCT CHARACTERISTICS
FOR
STANDARD GRADE 200 (SG-200)
AND
STANDARD GRADE 200X (SG-200X)

SG-200 and SG-200X are wet sheared, moderately-liberated fiber products for use as general purpose fillers. These dust-free pellets, which contain no binder are idealy suited for bulk handling and economical shifting and storage. SG-200 is approximately 1/4" in diameter and SG-200X is 1/8" in diameter for optimum dry blending.

Property	Typical Value
Reflectance (GE Brightness), %	68
Moisture Content, %	2
Magnetite, %	1.7
pH	9.5
Surface Area, m^2/g	60
Available Fiber Content, %	71
Ultimate Fiber Content, %	88
Packaged Density, $lbs./ft^3$	44
Single Bag Weight, lbs.	50
Single Pallet Weight, lbs.	2,000
50' Carload (60 pallets), lbs.	120,000
40' Truckload (20 pallets), lbs.	40,000

1573

PLAINTIFF'S EXHIBIT
UC-4498

7/73
Revised

X413422

Published by AsbestosClaims.Law
asbestosclaims.law/library/19065/2