PLAINTIFF'S EXHIBIT

UC-5057

WV-0010 #8
V76306A

BUSINESS CONFIDENTIAL
PRELIMINARY INFORMATION-
SUBJECT TO LATER VERIFICATION
OR REVISION

INFORMAL REPORT
PROJECT NO.: 132C40
DATE: October 4, 1974
AUTHOR(S): T. D. Foster, Jr.

10/4/74 P132C40 T. FOSTER, JR.

OIL PRODUCTION CHEMICALS: PHENOLIC RESIN COATED ASBESTOS FOR OIL BASE MUDS

Although oil base muds represent a relatively small fraction of the mud business, they are firmly established for certain specific jobs and as a result profit potential for specialty additives does exist for UCC. At present, UCC has very little business in this area; organic thickeners for the oil muds are usually of the tall oil acid soap type of molecule, together with blown asphalt and gilsonite. Inorganic types are quaternary amine-modified bentonites; e.g. Bentones.

As an outgrowth of work to prepare oleophillic minerals, specifically modification of UCC wet-process asbestos with silane, a suggestion was made to use a phenolic-coated asbestos being manufactured for other end uses. This report summarizes the test data obtained in an attempt to utilize this material for controlling the rheological properties of oil base muds.

Testing was performed in a diesel oil base containing 5 per cent water. The initial phenolic control resin sample, containing 7.0 percent resin, failed to have sufficient oleophillic properties and would not disperse. Two additional samples of material contained 10 and 20 percent phenolic (RG-144-10 and RG-144-20 respectively); these materials were prilled which is a definite aid to minimizing dusting of the fibers. Rheological properties are determined by standard API methods (1). Data are given in Table I. Static heat aging was accomplished in Baroid steel bombs in an air oven.

Both RG-144-10 and -20 (hereafter designated 10 and 20) require high speed shearing (Waring blender) but dispersed and suspended well. Some settling did occur but this is correctable by the customer by proper formulation of other ingredients. However, the settling does complicate the determination of 10 minute gel strength because the determined values are much lower than a well-suspended fluid should yield.

Rheologically, 10 and 20 are not as powerful thickeners as Bentone 34, based on apparent viscosities for a given additive concentration. Plastic viscosities are within the same general range as Bentone 34. The yield points and gel strengths of 10 and 20 exhibit significant difference when compared to Bentone 34. Oil muds have very strong thixotropic properties giving extremely high

RESEARCH AND DEVELOPMENT DEPARTMENT
CHEMICALS AND PLASTICS
UNION CARBIDE CORPORATION
SOUTH CHARLESTON, WEST VIRGINIA

yield points and gel viscosity. This is not a totally desirable characteristic. The high gel viscosity creates problems in restarting the drill string rotation, and when pulling the drill string the strong vacuum created can cause hole collapse. Conversely, sufficient yield and gel are required to lift and suspend cuttings. Fortunately, the yield points and gel viscosity for samples 10 and 20 are in a more favorable range than comparable muds made with Bentone 34. Both materials have sufficient gel viscosity to accept weighting material required to prepare high density muds.

Other laboratories have investigated coated minerals as potential oil mud thickeners and the materials failed because of thermal stability problems resulting from dissolution of the coating by the hot oil solvent. Anticipating this problem muds prepared from samples 10 and 20 were subjected to static heat aging at 200°F for 16 hours then 300°F for 16 hours with viscosity determinations made at intervals.

Under these test conditions, appreciable viscosity losses occurred with the asbestos muds but there are indications that the losses plateau at a usable level. Bentone 34 mud actually increased in viscosity with one sample resulting in an unworkable gel at 300°F. Although no gellation occurred with the asbestos samples, there appeared to be solution of part of phenolic coating; on a very long term basis for use as a packer fluid in hot wells the asbestos thickener may be inadequate.

CONCLUSIONS This preliminary study has shown that phenolic coated asbestos has sufficiently interesting rheological properties to warrant further study. A coating level of about 10 percent resin appears close to optimum. If the cost of the asbestos material can be held to less than Bentone 34, a decided advantage can be realized. The thermal stability of the asbestos-resin is decidedly inferior to silane modified asbestos for oil base muds. Because of our secrecy agreement with Dresser applicable to silane treated asbestos, consideration should be given to introducing the asbestos-resin product to Oil Base, Inc. who specialize in this technology.

T. D. Foster, Jr.


TDF:b

TABLE I

VISCOMETRIC PROPERTIES OF OIL BASE MUDS

Sample Type	Conc. lb/bbl	AP	PV	YP	Gel 10/10
RG-144-10	14	33.5	13	41	12-14
16 hrs/200°F		29.5	12	35	14-13
16 hrs/300°F		26.5	11	31	10-11
RG-144-10	11	22.3	10	24.5	8-11
16 hrs/200°		20	10	20	9-9
16 hrs/300°		18.5	10	17	6-6
RG-144-10	7	11.5	7	9	3.5-4.5
16 hrs/200°		10.5	7	7	3-3
16 hrs/300°		10	6	8	2.5-2.5
Bentone 34	14	82	12	140	95-117
16 hrs/200°F		122	9	226	182-190
16 hrs/300°F		Gelled			
Bentone 34	11	53.5	15	77	105-135
16 hrs/200°		64	6	116	91-91
16 hrs/300°		111	6	210	128-111
Bentone 34	7	18.5	8	21	21-21
16 hrs/200°		19	9	20	20-23
16 hrs/300°		29.5	10	39	28-29

Base Mud - 95% diesel, 5% water.


Bentone 34
RG-144-10,20
RG-144-10,20
Bentone 34
Apparent Viscosity, cp
Plastic Viscosity, cp
90
80
70
60
50
40
30
20
10
15
30
20
10
6
7
8
9
10
11
12
13
14
15
16
17
18